

Molybdenum containing scintillating bolometers for double-beta decay search (LUMINEU program)

D.V. Poda, L. Bergé, R.S. Boiko, M. Chapellier, D.M. Chernyak, N. Coron, F.A. Danevich, L. Devoyon, A.-A Drillien, L. Dumoulin, et al.

► **To cite this version:**

D.V. Poda, L. Bergé, R.S. Boiko, M. Chapellier, D.M. Chernyak, et al.. Molybdenum containing scintillating bolometers for double-beta decay search (LUMINEU program). 3rd French-Ukrainian workshop on the instrumentation developments for HEP, Oct 2015, Orsay, France. in2p3-01333292

HAL Id: in2p3-01333292

<http://hal.in2p3.fr/in2p3-01333292>

Submitted on 10 Jan 2020

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Molybdenum containing scintillating bolometers for double-beta decay search (LUMINEU program)

D.V. Poda^{a,b}, L. Bergé^a, R.S. Boiko^b, M. Chapellier^a, D.M. Chernyak^b, N. Coron^c,
F.A. Danevich^b, L. Devoyon^d, A.-A. Drillien^a, L. Dumoulin^a, C. Enss^e,
A. Fleischmann^e, L. Gastaldo^e, A. Giuliani^{a,f,g}, D. Gray^h, M. Gros^h, S. Hervé^h,
V. Humbert^a, I.M. Ivanovⁱ, A. Juillard^j, V.V. Kobychyev^b, F. Koskas^d, M. Loidl^k,
P. Magnier^h, E.P. Makarovⁱ, M. Mancuso^{a,f}, P. de Marcillac^a, S. Marnieros^a,
C. Marrache-Kikuchi^a, X.-F. Navick^h, C. Nones^h, E. Olivieri^a, B. Paul^h,
Y. Penichot^h, G. Pessina^{g,l}, O. Plantevin^a, T. Redon^c, M. Rodrigues^k,
V.N. Shlegelⁱ, O. Strazzer^d, M. Tenconi^a, L. Torres^c, V.I. Tretyak^{b,m},
Ya.V. Vasilievⁱ, M. Velazquezⁿ and O. Viraphongⁿ (LUMINEU Collaboration)

^aCSNSM, Univ. Paris-Sud, CNRS/IN2P3, Université Paris-Saclay, 91405 Orsay, France

^bInstitute for Nuclear Research, MSP 03680 Kyiv, Ukraine

^cIAS, CNRS, Univ. Paris-Sud, 91405 Orsay, France

^dCEA, Centre d'Etudes Saclay, Orphée, 91191 Gif-Sur-Yvette Cedex, France

^eInstitut für Angewandte Physik, Universität Heidelberg, D-69120 Heidelberg, Germany

^fDipartimento di Scienza e Alta Tecnologia dell'Università dell'Insubria, I-22100 Como, Italy

^gINFN, Sezione di Milano-Bicocca, I-20126 Milano, Italy

^hCEA, Centre d'Etudes Saclay, IRFU, 91191 Gif-Sur-Yvette Cedex, France

ⁱNikolaev Institute of Inorganic Chemistry, 630090 Novosibirsk, Russia

^jIPNL, Université de Lyon, Université Lyon 1, CNRS/IN2P3, 69622 Villeurbanne Cedex, France

^kCEA, LIST, Laboratoire National Henri Becquerel, 91191 Gif-Sur-Yvette Cedex, France

^lDipartimento di Fisica, Università di Milano-Bicocca, I-20126 Milano, Italy

^mINFN, Sezione di Roma, I-00185 Roma, Italy

ⁿICMCB, CNRS, Université de Bordeaux, 33608 Pessac Cedex, France

Abstract

A scintillating bolometer technology, promising to be used in a next-generation cryogenic experiment to search for neutrinoless double-beta decay, is currently under development within the LUMINEU (Luminescent Underground Molybdenum Investigation for Neutrino mass and nature) program. The recent results about the R&D of high quality large volume molybdenum containing crystal scintillators (zinc and lithium molybdates), including ones produced from ¹⁰⁰Mo-enriched powder, and aboveground / underground tests of cryogenic detectors based on these crystals are presented here.

Keywords: Double-beta decay, Scintillating bolometer, ZnMoO₄, Li₂MoO₄, Low background experiment, Radiopurity

1 Introduction

The recent discovery of neutrino oscillations (the Nobel prize award in physics 2015), phenomena which demonstrate that neutrinos have mass [1], stirs up an additional great interest in

the searches for neutrinoless double-beta ($0\nu 2\beta$) decay, a nuclear transformation of the type $(A, Z) \rightarrow (A, Z + 2) + 2e^-$. This never observed process is beyond the Standard Model (SM) and definitely requires finite value of neutrino mass, equivalence between neutrino and anti-neutrino (Majorana nature of neutrinos), and violation of the total lepton number by two units (see details in the recent review [2] and references herein).

The LUMINEU (Luminescent Underground Molybdenum Investigation for NEUtrino mass and nature) program [3, 4] is going to bridge the gap for high-sensitivity next-generation $0\nu 2\beta$ studies by the development of a technology based on Mo-containing scintillating bolometers, heat-light double read-out cryogenic calorimeters, and the demonstration of its feasibility by the successful realization of a small-scale experiment to search for $0\nu 2\beta$ decay of ^{100}Mo with zero background in the range of interest (around $Q_{2\beta} = 3034$ keV, the total energy of the two electrons emitted in $0\nu 2\beta$ decay of ^{100}Mo). It will play an important role in the selection for the technology to be adopted for a tonne-scale cryogenic $0\nu 2\beta$ experiment within the CUPID (CUORE Upgrade with Particle IDentification) project [5]. The main R&D results in the framework of the LUMINEU program are briefly presented here.

2 R&D of scintillating bolometers within LUMINEU

2.1 Tasks of the LUMINEU program

LUMINEU is performing an extensive R&D of Mo-containing scintillating bolometers which involves several general tasks related with: I) crystal scintillators; II) light detectors; III) temperature sensors; IV) prototypes of scintillating bolometers; V) final detectors for a pilot $0\nu 2\beta$ experiment. Below we describe briefly the program and the main requirements of these tasks.

A high detection efficiency for $0\nu 2\beta$ decay can be obtained in an experiment with the so-called “active-source” technique for which a $0\nu 2\beta$ source (e.g. ^{100}Mo) is embedded into a detector. The baseline detector material for LUMINEU is a zinc molybdate (ZnMoO_4) scintillator, however another promising Mo-based material, lithium molybdate (Li_2MoO_4), is also under consideration. Therefore, task I is devoted to the development of purification and crystallization procedures for producing large volume, high optical quality, radiopure scintillators both from natural and ^{100}Mo -enriched molybdenum. In view of the high cost of enriched ^{100}Mo and the prospect to grow ~ 1000 crystals (for a large-scale project), one needs to optimize a production line in order to get high throughput and low irrecoverable losses of the enriched material. Specifying these requirements, the main objectives are scintillators with a mass of ~ 1 kg (scintillation elements up to 0.4 kg) produced with more than 70% crystal yield, a few % of irrecoverable losses, and with a level of internal radioactive contamination by ^{228}Th and ^{226}Ra ≤ 0.01 mBq/kg (the total alpha activity of radionuclides from U/Th, except that of ^{210}Po , is below 1 mBq/kg).

The main background source above 2615 keV in a bolometric $0\nu 2\beta$ experiment is caused by α decays of natural radioactivity. Usually, a scintillator produces less light for α particles with respect to $\gamma(\beta)$'s of the same energy (this phenomenon is known as quenching). Therefore, by using a light detector complementary to a bolometer which scintillates at low temperature, one can efficiently discriminate an α -induced background. It is convenient to make this light detector as a thin bolometer and mount it close to a scintillator-based bolometer, which all

together constitute a scintillating bolometer. Therefore, task II includes the fabrication of optical bolometers from high purity Ge wafers, widely used for this purpose. An important part of the activity within this task is dedicated to the optimization of light detectors with the aim to get an acceptable performance. Since both ZnMoO_4 and Li_2MoO_4 scintillators are characterized by very modest light yield (of the order of ~ 1 keV per 1 MeV deposited energy), efficient light collection and absorption are important parameters. The energy resolution (FWHM) of the photodetector should be good enough to provide a 99.9% discrimination between light signals caused by ~ 3 MeV $\gamma(\beta)$ and α particles impinging in the Mo-based scintillator. In particular, an α/γ separation at the level of 5σ at ~ 3 MeV can be achieved with a light detector characterized by FWHM $\sim 15\%$ at 5.9 keV X-ray of ^{55}Fe (typically used for calibration of these devices) [6]. Finally, random coincidences of two neutrino double-beta decay of ^{100}Mo , allowed in the SM process and registered with a half-life $\sim 10^{18}$ yr [1], can constitute a major background for a bolometric $0\nu 2\beta$ experiment with Mo-containing scintillators, as it was pointed out for the first time in Ref. [7]. Therefore a light detector should have a fast response (e.g. a rise time ~ 1 ms or less) and an as high as possible signal-to-noise ratio to provide an efficient discrimination of random coincidences.

A small temperature rise appeared after particle interaction inside a bolometer can be measured by a dedicated thermometer. Within task III, LUMINEU is developing three technologies of temperature sensors: Neutron Transmutation Doped (NTD) Ge thermistors [8], superconducting Transition-Edge Sensors (TES) [9], and Magnetic Metallic Calorimeters (MMC) [10]. The first two types exploit the dependence of resistivity on temperature, while the last one that of magnetization on temperature. All results given below were obtained with scintillating bolometers instrumented with NTD Ge-based thermometers.

Task IV involves the construction of small / middle size prototypes of scintillating bolometers and their low temperature test, below tens mK, both at aboveground (at CSNSM) and underground (at Modane in France and Gran Sasso in Italy) cryogenic facilities. The crucial point of this activity is achieving excellent performance of Mo-containing scintillating bolometers in terms of energy resolution (FWHM ≤ 10 keV at 3 MeV) and particle identification (α/γ separation more than 99.9%), as well as proving low bulk radioactive contamination of crystals.

Task V requires the fabrication of at least two complete single modules based on massive ZnMoO_4 crystals (with mass up to 0.4 kg; one produced from natural molybdenum and another one enriched in ^{100}Mo), and a realization of a pilot experiment with the aim to demonstrate the abovementioned key performance and radiopurity, which are associated with a zero-background $0\nu 2\beta$ experiment. Current status of the LUMINEU tasks are briefly summarized below (task III will not be highlighted here in more detail than it was done above).

2.2 R&D and performance of Mo-containing scintillating bolometers

A technology of fabrication of large area light detectors (with diameter up to 50 mm and thickness around 250 μm) from high purity germanium wafers (Umicore, Belgium) was developed at CSNSM (Orsay, France) [6]. The adopted LUMINEU standard is a $\varnothing 44$ -mm Ge slab coated by SiO to improve light absorption [11]. In addition to the batch of the LUMINEU NTD Ge-based light detectors, photodetectors produced within the LUCIFER $0\nu 2\beta$ project [12], as well as state-of-the-art extra thin (~ 30 – 50 μm) germanium optical bolometers developed at IAS (Orsay, France) [13] were used to build and test LUMINEU scintillating bolometers. First test

of MMC-based light detectors developed within LUMINEU [14] demonstrate their potential to get ~ 100 times faster response than that typical for NTD Ge-based photodetectors.

A dedicated protocol for molybdenum purification (double sublimation of molybdenum oxide in vacuum and double recrystallization of ammonium molybdate from aqueous solutions) has been adopted by LUMINEU to get high purity initial compound for crystal growth [4]. The chosen advanced directional solidification method developed at NIIC (Novosibirsk, Russia), low-thermal-gradient Czochralski (LTG Cz) technique, demonstrates the possibility to grow large (up to 1.5 kg) ZnMoO_4 crystals with a high crystal yield ($\sim 80\%$ of charge) [4]. The aboveground low temperature test of first LUMINEU crystals (scintillation elements with size of $\varnothing 20 \times 40$ mm and $\varnothing 35 \times 40$ mm and masses of 55 g and 160 g respectively), produced from ZnMoO_4 boules grown from deeply purified materials, shows excellent signal-to-noise ratio, high signal amplitude, expected values of light-to-heat ratio and light quenching factor for α particles [4]. Only internal ^{210}Po contaminant was clearly observed over about two weeks of data taking which indicates high crystals' radiopurity and effectiveness of the purification procedure.

Advances in large volume ZnMoO_4 growth have been achieved by applying double crystallization. In particular, by using this technique an improved quality ~ 1.0 kg boule was grown from molybdenum purified by double recrystallization [15]. Two ZnMoO_4 optical elements produced with a size expected for a pilot LUMINEU $0\nu 2\beta$ experiment ($\varnothing 50 \times 40$ mm; masses 336 and 334 g) were used to construct identical scintillating bolometers [16] according to a new special design compatible with the EDELWEISS set-up at the Modane underground laboratory (LSM, France). Results of long term (about 3000 h) low background measurements with these devices [15, 17] demonstrate an excellent energy resolution (e.g. FWHM ~ 9 keV at 2615 keV) and an efficient α/γ separation (15σ above 2.5 MeV) achieved with ZnMoO_4 -based scintillating bolometers, as well as very high internal radiopurity of ZnMoO_4 crystals (e.g. activity of ^{228}Th and $^{226}\text{Ra} \leq 0.004$ mBq/kg), which completely satisfy the LUMINEU requirements and those of a future large-scale experiment. An illustration of the main performance of a 334-g ZnMoO_4 detector is shown in Fig. 1. Taking into account that the additional crystallization improves quality of a crystal boule and could also enhance bulk radiopurity thanks to segregation of radionuclides during growing process, double crystallization can be used for the production of large LUMINEU crystals.

A first ^{100}Mo -enriched $\text{Zn}^{100}\text{MoO}_4$ crystal with a mass of ~ 0.17 kg has been successfully developed with 84% crystal yield and $\sim 4\%$ irrecoverable losses of the enriched material [18]. The used $^{100}\text{MoO}_3$ (99.5% enrichment in ^{100}Mo) was purified by sublimation in vacuum and double recrystallization from aqueous solutions. Molybdenum purification is related with the major part of losses (85%) and the minor part with the crystal growth. The $\text{Zn}^{100}\text{MoO}_4$ boule had a non-regular shape and yellow coloration unlike similar size natural ZnMoO_4 crystals. It is caused by still existing difficulties during the solidification, in particular by the effect of a second phase formation. A $\text{Zn}^{100}\text{MoO}_4$ scintillating bolometer array, built from two produced small $\text{Zn}^{100}\text{MoO}_4$ elements (59 g and 63 g) and tested aboveground, shows bolometric properties similar to non-enriched ZnMoO_4 detectors [18]. The energy resolution of both bolometers was reasonably good taking into account a high counting rate due to the background conditions of the sea-level laboratory. In particular, 5 and 10 keV FWHM at 609 keV γ 's of ^{214}Bi from environmental radioactivity was obtained with the 59-g and 63-g $\text{Zn}^{100}\text{MoO}_4$ bolometers respectively [18]. After 42 h of data taking only a hint associated with ^{210}Po was observed in the α region, which implies encouraging radiopurity of the crystals [18]. During an underground




Figure 1: (Top) A 2-D histogram showing light-to-heat ratio versus heat for the data of the 14-h ^{232}Th calibration measurements with the 334-g ZnMoO_4 -based scintillating bolometer operated in the EDELWEISS set-up at LSM. A high potential of full separation between α events and $\gamma(\beta)$ band (red and blue dots respectively) is clearly evident. The region, where events caused by decays of α radionuclides from U/Th (above 4 MeV) are expected, is mainly populated by ^{210}Po , which demonstrates encouraging internal radiopurity. (Bottom) 1-D projection of the 2-D histogram shown at the figure top. Energies of γ quanta are given in keV.

test at LSM, the $\text{Zn}^{100}\text{MoO}_4$ array which had a non-standard holder was strongly affected by a microphonic noise deteriorating the detector's energy resolution. It is caused by the absence of a suspension system in the EDELWEISS set-up (to be implemented soon), which can reduce effect of microphonics, in contrast to the cryostat [19] used for the aboveground measurements. Anyway, a full particle identification by $\text{Zn}^{100}\text{MoO}_4$ detectors was clearly demonstrated in the underground test.

The ZnMoO_4 solidification procedure was further improved by introducing a small amount of tungsten oxide (up to ~ 0.5 wt%) to stabilize the melt and several high quality ~ 0.15 -kg crystal boules were grown. No effect of W-doping on bolometric properties of ZnMoO_4 was evidenced by the aboveground measurements with a scintillating bolometer array constructed from stoichiometric and W-doped ZnMoO_4 crystals ($\varnothing 20 \times 40$ mm each) [20].

Recently, a first large volume colorless $\text{Zn}^{100}\text{MoO}_4$ crystal (~ 1.4 kg) has been developed [17, 21]. Two large scintillation elements were produced with a shape of hexagonal prism (with diagonal 60 mm and height 40 mm, masses 379 g and 382 g) in order to have an improved light output according to studies [22]. Massive $\text{Zn}^{100}\text{MoO}_4$ -based scintillating bolometers have been tested in the CUORE R&D test cryostat at Gran Sasso National Laboratories (LNGS, Italy) and the data analysis is in progress. A new test in the EDELWEISS set-up at Modane is foreseen. Meanwhile, background conditions of a middle-scale $0\nu 2\beta$ experiment with 48

$\text{Zn}^{100}\text{MoO}_4$ scintillating bolometers ($\varnothing 60 \times 40$ mm, 495 g each) installed in the EDELWEISS set-up have been simulated with GEANT4-based code [21]. Considering the already achieved performance, radiopurity, and pulse-shape discrimination of random coincidences developed by LUMINEU [23], a background counting rate $\approx 5 \times 10^{-4}$ counts/yr/kg/keV at $Q_{2\beta}$ of ^{100}Mo , corresponding to zero-background conditions, can be reached [21].

In spite of the achieved progress in the development of large $\text{Zn}^{100}\text{MoO}_4$, growing a regular cylindrical shape crystal boule with similar quality along its length is still a difficult task (e.g. see Fig. 1 in [17]). This problem can be resolved, without further R&D, just by pulling a short crystal boule. Another solution could be related with a choice of another Mo-based material, Li_2MoO_4 , which is characterized by comparatively easy crystal growth process and has bolometric properties similar to ZnMoO_4 . In particular, several perfect quality Li_2MoO_4 crystal boules with masses 0.1–0.4 kg were grown by LTG Cz method from deeply purified Mo and commercial Li_2CO_3 (99.99% purity grade) [24]. A first large Li_2MoO_4 -based ($\varnothing 40 \times 40$ mm, 151 g) scintillating bolometer was tested aboveground with quite encouraging results [24], which were reinforced by subsequent ~ 350 -h underground measurements at LNGS [25]. In particular, an excellent spectrometric properties (FWHM ~ 4 keV at 2615 keV), an efficient particle identification and high radiopurity for U/Th nuclides (^{228}Th and $^{226}\text{Ra} \leq 0.02$ mBq/kg) were obtained [25]. There is only an issue caused by considerably high activity of ^{40}K inside the tested crystal (~ 60 mBq/kg), which can be a problem due to random coincidences in a future $0\nu 2\beta$ experiment. Fortunately, this issue can be easily resolved by selection of a Li-containing raw material with low concentration of ^{40}K and by recrystallization of Li_2MoO_4 crystals. It is worth to note that two scintillating bolometers based on large Li_2MoO_4 crystals ($\varnothing 50 \times 40$ mm, 242 g each) produced from different Li-based powder with low ^{40}K content (tested by HPGe γ spectroscopy) are under investigation in order to prove low bulk activity of ^{40}K . A Li-powder with the lowest ^{40}K content will be used to produce a first $\text{Li}_2^{100}\text{MoO}_4$ crystal. A dedicated low temperature test will be performed in order to completely demonstrate that Li_2MoO_4 -based scintillating bolometer is a viable detector for a large-scale cryogenic $0\nu 2\beta$ experiment.

3 Conclusions

A protocol for producing high quality large volume Mo-containing crystal scintillators from deeply purified molybdenum with both natural isotopic composition and enriched in ^{100}Mo has been developed within the LUMINEU program. A technology for the development of high performance LUMINEU single modules based on radiopure large ZnMoO_4 and Li_2MoO_4 crystals is well established providing high energy resolution (better than 10 keV FWHM at 2615 keV), efficient α/γ separation (more than 5σ) and required low level of bulk radioactivity (e.g. ^{228}Th and $^{226}\text{Ra} \sim 0.01$ mBq/kg). A first large $\text{Zn}^{100}\text{MoO}_4$ crystal (~ 1.4 kg) was successfully grown and two 0.4-kg $\text{Zn}^{100}\text{MoO}_4$ -based scintillating bolometers have been preliminary tested at LNGS (Italy). The development of a first large $\text{Li}_2^{100}\text{MoO}_4$ crystal scintillator is in progress and a pilot LUMINEU test of massive $\text{Zn}^{100}\text{MoO}_4$ - and $\text{Li}_2^{100}\text{MoO}_4$ -based scintillating bolometers in the EDELWEISS set-up at LSM (France) is foreseen at the beginning of 2016. After completing this test we will make a final choice about the Mo-containing crystals to be produced from ~ 10 kg of ^{100}Mo (enriched isotope is already available) for a middle-scale $0\nu 2\beta$ experiment (LUCINEU project) based on the LUMINEU technology. A Monte Carlo simulation of 48 0.5-kg $\text{Zn}^{100}\text{MoO}_4$ -based scintillating bolometers installed in the EDELWEISS set-up demonstrates

the possibility to get a satisfactory low background counting rate in the range of interest (at ~ 3 MeV). The LUMINEU activity is now part of the CUPID project, a proposed bolometric tonne-scale $0\nu 2\beta$ experiment experiment to be built as a follow-up to CUORE and exploiting as much as possible the CUORE infrastructures.

4 Acknowledgements

This work is part of the LUMINEU project funded by the Agence Nationale de la Recherche (ANR, France). The Li_2MoO_4 aboveground test was performed with the determinant contribution of ISOTTA, a R&D ASPERA common call. The Ukrainian group was supported in part by the IDEATE International Associated Laboratory (LIA). DVP was supported by the P2IO LabEx (ANR-10-LABX-0038) in the framework “Investissements d’Avenir” (ANR-11-IDEX-0003-01) managed by the ANR (France).

References

- [1] K.A. Olive et al. (Particle Data Group), *Review of Particle Physics*, Chin. Phys. C 38 (2014) 090001 and 2015 update.
- [2] S.M. Bilenky, C. Giunti, *Neutrinoless double-beta decay: A probe of physics beyond the Standard Model*, Int. J. Mod. Phys. A 30 (2015) 1530001.
- [3] M. Tenconi for the LUMINEU collaboration, *LUMINEU: a pilote scintillating bolometer experiment for neutrinoless double beta decay search*, Phys. Proc. 61 (2015) 782.
- [4] L. Bergé et al., *Purification of molybdenum, growth and characterization of medium volume ZnMoO_4 crystals for the LUMINEU program*, JINST 9 (2014) P06004.
- [5] G. Wang et al. (The CUPID Interest Group), *CUPID: CUORE (Cryogenic Underground Observatory for Rare Events) Upgrade with Particle Identification*, arXiv:1504.03599 [physics.ins-det] (2015);
G. Wang et al. (The CUPID Interest Group), *R&D towards CUPID (CUORE Upgrade with Particle Identification)*, arXiv:1504.03612 [physics.ins-det] (2015).
- [6] M. Tenconi, *Development of luminescent bolometers and light detectors for neutrinoless double beta decay search*, Ph.D. thesis, University Paris-Sud, Orsay, France (2015).
- [7] J.W. Beeman et al., *A next-generation neutrinoless double beta decay experiment based on ZnMoO_4 scintillating bolometers*, Phys. Lett. B 710 (2012) 318.
- [8] X.-F. Navick et al., *NTD-Ge development in the LUMINEU project for Rare Events searches with cryogenic detectors*, Talk given at 16th Int. Workshop on Low Temperature Detectors (LTD-16), Grenoble, France, 20–24 July 2015.
- [9] C. Nones et al., *High-impedance NbSi TES sensors for studying the cosmic microwave background radiation*, Astron. & Astrophys. 548 (2012) A17.

- [10] M. Loidl et al., *Concept of metallic magnetic calorimeters for rare event search in the LUMINEU project*, J. Low Temp. Phys. 176 (2014) 624.
- [11] M. Mancuso et al., *An experimental study of antireflective coatings in Ge light detectors for scintillating bolometers*, EPJ Web Conf. 65 (2014) 04003.
- [12] J.W. Beeman et al., *Characterization of bolometric Light Detectors for rare event searches*, JINST 8 (2013) P07021.
- [13] N. Coron et al., *Highly sensitive large-area bolometers for scintillation studies below 100 mK*, Opt. Eng. 43 (2004) 1568.
- [14] D. Gray et al., *A large area light detector for scintillators in rare event searches developed in the LUMINEU context*, Talk given at 16th Int. Workshop on Low Temperature Detectors (LTD-16), Grenoble, France, 20–24 July 2015.
- [15] E. Armengaud et al. (the LUMINEU and the EDELWEISS collaborations), *Development and underground test of radiopure $ZnMoO_4$ scintillating bolometers for the LUMINEU $0\nu 2\beta$ project*, JINST 10 (2015) P05007.
- [16] D.V. Poda for the LUMINEU and the EDELWEISS Collaborations, *Scintillating bolometers based on $ZnMoO_4$ and $Zn^{100}MoO_4$ crystals to search for $0\nu 2\beta$ decay of ^{100}Mo (LUMINEU project): first tests at the Modane Underground Laboratory*, Accepted for publication in Nucl. Part. Phys. Proc., DOI: 10.1016/j.nuclphysbps.2015.09.290; arXiv:1502.01161 [physics.ins-det] (2015).
- [17] D.V. Poda et al., *Radiopure $ZnMoO_4$ scintillating bolometers for the LUMINEU double-beta experiment*, AIP Conf. Proc. 1672 (2015) 040003.
- [18] A.S. Barabash et al., *Enriched $Zn^{100}MoO_4$ scintillating bolometers to search for $0\nu 2\beta$ decay of ^{100}Mo with the LUMINEU experiment*, Eur. Phys. J. C 74 (2014) 3133.
- [19] M. Mancuso et al., *An aboveground pulse-tube-based bolometric test facility for the validation of the LUMINEU $ZnMoO_4$ crystals*, J. Low Temp. Phys. 176 (2014) 571.
- [20] D.M. Chernyak et al., *Effect of tungsten doping on $ZnMoO_4$ scintillating bolometer performance*, Opt. Mater. 49 (2015) 67.
- [21] F.A. Danevich et al., *Status of LUMINEU program to search for neutrinoless double beta decay of ^{100}Mo with cryogenic $ZnMoO_4$ scintillating bolometers*, AIP Conf. Proc. 1686 (2015) 020007.
- [22] F.A. Danevich et al., *Optimization of light collection from crystal scintillators for cryogenic experiments*, Nucl. Instrum. Meth. A 741 (2014) 41.
- [23] D.M. Chernyak et al., *Rejection of randomly coinciding events in $ZnMoO_4$ scintillating bolometers*, Eur. Phys. J. C 74 (2014) 2913.
- [24] T.B. Bekker et al., *Aboveground test of an advanced Li_2MoO_4 scintillating bolometer to search for neutrinoless double beta decay of ^{100}Mo* , Astropart. Phys. 72 (2016) 38.

- [25] L. Pattavina, *Scintillating bolometers of LMO in LNGS*, Talk given at fourth and final general meeting of the ISOTTA project, Orsay, France, 1–2 December 2014.